

GRAFTED OREVAC®

Adhesive Resins for packaging applications

Orevac grades for PE structures

Grade	Base polymer	MFI (190°C / 2,16Kg)	Vicat point (°C)	Process				Adhesion to
				Blown film	Cast Film	Blow Molding	Sheet	
18334	LLDPE	1	101			⊙		PE, PA, EVOH
18365	LLDPE	2,5	90	⊙	⊙	⊙		PE, PA
18360	LLDPE	2	87	⊙		⊙		PE, PA, EVOH
18370	LLDPE	2	83		⊙			PE, PA, EVOH
18380	LLDPE	4	83		⊙			PE, PA, EVOH
18211	EVA	3,5	51	⊙			⊙	PE, PA, EVOH, PS, PET
18910	LLDPE	1,5	77	⊙			⊙	PE, PS, EVOH, PA

Orevac grades for PP structures

Grade	Base polymer	MFI (230°C / 2,16Kg)	Vicat point (°C)	Process					Adhesion to
				Blown film	Cast Film	Blow Molding	Sheet	Extrusion coating	
18729	Homo PP	4,5	137			⊙	⊙		PP, PA, EVOH
18722	Random PP	8	120	⊙	⊙				PP, PA, EVOH
18750	Homo PP	35	121					⊙	PP, PA, EVOH, Alu
18751	Homo PP	37	138					⊙	PP, PA, EVOH, Alu

September 2010

The information contained in this document is based on trials carried out by our Research Centres and data selected from the literature, but shall in no event be held to constitute or imply any warranty, undertaking, express or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by ARKEMA with regard to the handling, processing or use of the product or products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.

